

AMBERLYST™ 36DRY

Industrial Grade Strongly Acidic Catalyst

Introduction

AMBERLYST 36DRY is a bead form, macroreticular, sulfonic acid ion exchange resin developed particularly for heterogeneous catalysis.

The special process used to manufacture AMBERLYST 36DRY results in a particularly high concentration of acid groups and also confers an improved thermal stability when compared to catalysts with a similar level of crosslinking. It is also less prone to the polymer fouling.

AMBERLYST 36DRY is mainly used in the phenol alkylation processes.

Properties

Physical form	Opaque beads
lonic form as shipped	Hydrogen
Concentration of acid sites	≥ 5.40 eq/kg
Water content	≤1.65%
Shipping weight	770 g/L (48 lbs/ft ³)
Particle size	
Fines content	< 0.300 mm: 5.0% max
Coarse beads	> 1.180 mm: 5.0% max
Nitrogen BET	0.550 to 0.700 mm
Surface area	33 m ² /g
Average pore diameter	240 Å
Total pore volume	0.20 cc/g
Swelling	Dry to phenol: 20%

Suggested Operating Conditions

Maximum operating temperature	150°C (300°F)
Minimum bed depth	600 mm (24 inches)
Operating flow rate	1 to 5 BV*/h (LHSV)
Pressure drop limitation	1 bar (15 psig) across the bed

For more information about DOW™ resins, call the Dow Water & Process Solutions business:

 North America:
 1-800-447-4369

 Latin America:
 (+55) 11-5188-9222

 Europe:
 +800-3-694-6367

 Italy:
 +800-783-825

 South Africa:
 +0800 99 5078

 Pacific:
 +8007776 7776

 China:
 +400 889-0789

 http://www.dowwaterandprocess.com

Notice: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

