

### PRODUCT DATA SHEET

AMBERLITE SR1L Na is a gel type strong acid cation exchange resin of the sulphonated polystyrene type, used for water softening. Its principal characteristics are excellent physical, chemical and thermal stability, good ion exchange kinetics and high exchange capacity. AMBERLITE SR1L Na has been specially developed for potable

water and food applications (i.e. decalcification of saccharose thin juice) following a special manufacturing process which does not use any solvents. AMBERLITE SR1L Na is produced in a free flowing form which makes the filling of the units and cartridges very easy and rapid.

#### **PROPERTIES** Styrene divinylbenzene copolymer Matrix Functional groups\_\_\_\_\_ **Sulphonates** Physical form\_\_\_\_\_ Amber beads Total exchange capacity [1] \_\_\_\_ $Na^{\dagger}$ Moisture holding capacity [2]\_\_\_\_\_\_\_Shipping weight 2.05 eq/L (Na<sup>+</sup> form) 41 to 49 % (Na<sup>+</sup> form) Shipping weight \_\_\_\_\_ $820 \, g/L$ Harmonic mean size\_\_\_\_\_ 600 - 800 μm Uniformity coefficient \_\_\_\_\_\_ ≤ 1.8 Fines content [2] < 0.300 mm : 2.0 % max Coarse beads > 1.180 mm : 2.0 % max Chemical resistance Insoluble in dilute solutions of acids or bases and common solvents [1] Average value calculated from statistical quality control. [2] Contractual value. Test methods and SQC charts are available on request.

# SUGGESTED OPERATING CONDITIONS (WATER TREATMENT)

| Maximum operating temperature | 120 °C                         |           |           |
|-------------------------------|--------------------------------|-----------|-----------|
| Service Flow rate             | 5 to 50* BV/h                  |           |           |
| Regenerants                   | NaCl                           | HCl       | $H_2SO_4$ |
| Level (g/L)                   | 60 to 250                      | 50 to 150 | 50 to 240 |
| Concentration (%)             | 10                             | 5 to 8    | 0.7 to 6  |
| Flow rate (BV/h)              | 2 to 8                         | 2 to 5    | 2 to 20   |
| Minimum contact time          | 30 minutes                     |           |           |
| Slow rinse                    | 2 BV at regeneration flow rate |           |           |
| Fast rinse                    | 2 to 4 BV at service flow rate |           |           |
|                               |                                |           |           |

<sup>\*1</sup> BV (Bed Volume) = 1 m3 solution per m3 resin

#### **COMPLIANCE**

AMBERLITE SR1L Na is approved in France, Austria, Poland, the UK for the treatment of potable water. It complies with the Council of Europe Resolution AP(97)1, and with US FDA 21 CFR 173.25 (a). All ingredients entering the composition in AMBERLITE SR1L Na are listed in German BgVV XXIV recommendation\*, provided it has been preaccording to Rohm treated and recommendations.

AMBERLITE SR1L Na is approved by la Direction Générale de la Concurrence, de la Consommation et de la Répression des Fraudes in France as sugar industry processing aid.

details further regarding registrations/compliances, please contact your nearest Rohm and Haas office.

\* in Germany complies with DIN 19633 (<10 ppm TOC).

Fig. I: Bed Expansion 5°C 10°C 150 20°C 125 30°C 100 =xpansion 40°C 75 60°C 50 25

20

Vitesse de soulèvement

### **QUALITY CONTROL**

AMBERLITE SR1L Na is analysed to ensure its compliance with high purity specification, particular:

- Physical and chemical properties,
- Individual release of certain substance in the treated water.
- Global release of organic substances expressed in TOC (Total Organic Carbon),
- Total microbial count.

## HYDRAULIC CHARACTERISTICS

# (Water Treatment)

Figure 1 shows the bed expansion of AMBERLITE SR1L Na, as a function of backwash flow rate and water temperature.

Figure 2 shows the pressure drop data for AMBERLITE SR1L Na, as a function of service flow rate and water temperature.




Fig. 2: Pressure drop

All our products are produced in ISO 9002 certified manufacturing facilities.

30 m/h

Rohm and Haas/Ion Exchange Resins - Philadelphia, PA - Tel. (800) RH AMBER - Fax: (215) 537-4157 Rohm and Haas/Ion Exchange Resins - 75579 Paris Cedex 12 - Tel. (33) 1 40 02 50 00 - Fax: 1 43 45 28 19

WEB SITE: http://www.rohmhaas.com/ionexchange



AMBERLITE is a trademark of Rohm and Haas Company, Philadelphia, U.S.A.

AMBERLITE is a trademark of Rohm and Haas Company, Philadelphia, U.S.A. Ion exchange resins and polymeric adsorbents, as produced, contain by-products resulting from the manufacturing process. The user must determine the extent to which organic by-products must be removed for any particular use and establish techniques to assure that the appropriate level of purity is achieved for that use. The user must ensure compliance with all prudent safety standards and regulatory requirements governing the application. Except where specifically otherwise stated, Rohm and Haas Company does not recommend its ion exchange resins or polymeric adsorbents, as supplied, as being suitable or appropriately pure for any particular use. Consult your Rohm and Haas technical representative for further information. Acidic and basic regenerant solutions are corrosive and should be handled in a manner that will prevent eye and skin contact. Nitric acid and other strong oxidising agents can cause explosive type reactions when mixed with Ion Exchange resins. Proper design of process equipment to prevent rapid buildup of pressure is necessary if use of an oxidising agent such as nitric acid is contemplated. Before using strong oxidising agents in contact with Ion Exchange Resins, consult sources knowledgeable in the handling of these materials.

Rohm and Haas Company makes no warranties either expressed or implied as to the accuracy or appropriateness of this data and expressly excludes any liability upon Rohm and Haas arising out of its use. We recommend that the prospective users determine for themselves the suitability of Rohm and Haas materials and suggestions for any use prior to their adoption. Suggestions for uses of our products of the inclusion of descriptive material from patents and the citation of specific patents in this publication should not be understood as recommending the use of our products in violation of any patent or as permission or license to use any patents of the Rohm and Haas Company. Material Safety Data Sheets outlining the hazards and handling methods for our products are available on request.

©2000 Rohm and Haas Company PDS 0537 A - Oct. 97 - 2/2